

Product Data Sheet

CEMROK GP MORTAR

CONSTRUCTION AND INSTALLATION GROUTS

Description

Cemrok GP Mortar is a quick and easy to use sand and cement mortar suitable for a wide range of applications.

Uses

Cemrok GP Mortar can be used in the following applications

- Brick Laying.
- Block Paving.
- Pointing.
- Rendering & Patching.
- General Repairs.

Special Properties

- Grey colour when dry.
- Ready to use: Just add water.
- Interior & exterior use.
- Consistent & durable results.

Coverage

The following are approximate yields:

70 x 25kg bags are required to produce 1m³ of mortar.

1 x 25kg bags will produce enough mortar to lay 25 standard house bricks.

1 x 25kg bag will produce 1.25m² of render at 10mm thick

Preparation and Priming

Ensure any loose material is removed prior to application of the mortar. When repairing pointing joints the depth of the joint should be twice the width. To help prevent the mixed mortar drying out too quickly, dampen bricks, blocks and bases before proceeding. Brush any loose debris from the surface of the area prior to use.

Mixing

Empty the product onto a clean, flat surface. Create a pile of mortar with a hollow in the top. Add small amounts of clean water into the hollow ensuring that it does not run down the edges. Shovel or trowel the contents in the water. When all the water disappears, create

another hollow and repeat. Continue to add more water until the consistency required is achieved (approximately 3 litres per 25kg bag). Avoid adding too much water as this will weaken the mortar mix and affect the strength and setting time.

Cemrok GP Mortar should be mixed using water that complies with BS EN 1008 (as for concrete).

Application

On completion, cover newly laid masonry with plastic sheet or hessian to protect from weather hazards until fully set. Do not apply in temperatures below 5°C or above 25°C. Frost free conditions are required during curing.

Quality Control

All Pozament products are factory blended, tested and packaged to quality control procedures in accordance with BS EN ISO 9001.

Clean up and Spillages

Dry powders should be swept up and disposed of in accordance with the Local Authority.

Packaging and Storage

Cemrok GP Mortar is available in nominally 25kg sacks, palletised and shrink-wrapped.

Cemrok GP Mortar should be stored in cool dry areas clear of the ground sheeted or under cover and stacked not more than two pallets high.

The product should be used on a first in – first out basis.

Shelf life is minimum 6 months but could be in excess of 9 months subject to temperature and humidity.

Information, prices & ordering

For technical information, pricing and to place orders contact our Sales Office on the following:

Telephone: **08444 630046** Fax: **08443 099703**

Email: pozament@tarmac.co.uk

Visit our website: www.pozament.co.uk

Pozament - Tarmac Building Products Ltd.,
Swains Park Industrial Estate, Park Road,
Overseal, Swadlincote, Derbyshire DE12 6JT.

Health & Safety

Health and safety advice, which must be followed, can be found on the Material Safety Data Sheet. Users are advised to wear face mask, goggles, gloves and overalls when handling, mixing and applying cementitious products.

Contains Portland Cement. Contains Chromium (VI), which may produce an allergic reaction. Clothing contaminated by wet cement should be removed immediately and washed before reuse. R38 - Irritating to skin. R41 - Risk of serious damage to eyes. S26 - In case of contact with eyes, rinse immediately with water and seek medical advice. S37/39 - Wear suitable gloves and eye/face protection. S2 - Keep out of reach of children