

TECHNICAL INFORMATION

PQ-X CONCRETE MIX DESIGN

Product Data Sheet: Concrete Repair & Installation

MIX DESIGN INFORMATION

The below table describes the recommended mix design ratios to achieve the technical performance stated in the **PQ-X Cement** technical datasheet.

Ingredient	Mix Design
PQ-X Cement	455
4/20 Aggregate	1085
0/4 Washed Concrete Sand	660
Water: Cement Ratio	0.37-0.38

The above mix design is based on land sourced 0/4 washed concrete sand and 4/20 aggregate from Tyttenhanger quarry.

These figures are provided as guidelines only and may need to be adjusted due to site conditions and moisture content of the sand and aggregate used to achieve an S4 concrete slump classification (160-210mm).

INFORMATION, PRICES & ORDERING

For technical information, pricing and to place orders contact our Sales Office on the following:

Telephone: **03444 630 046**

Email: pozament@tarmacbp.co.uk

Visit our website: Pozament.co.uk

Tarmac Building Products Ltd.

Swains Park Industrial Estate, Park Road, Overseal,
Swadlincote, Derbyshire, DE12 6JT

For more details contact:
03444 630 046 pozament@tarmacbp.co.uk

The information given in this technical data sheet is based on our current knowledge and is intended to provide general notes on our products and their uses. Tarmac endeavour to ensure that the information given is accurate, but accept no liability for its use or its suitability for particular application because of the product being used by the third party without our supervision. Any existing intellectual property right must be observed.